

AME 8060-1



Vacuum Casting (VC)
Material Datasheet



Similar to PP/PE. Suitable for prototypes and technical parts.

Measurement	Value
Shore Hardness	80D
Tensile Strength	47 MPa
Tensile Modulus	1,225 MPa
Flexural Strength	60 MPa
Flexural Modulus	1,310 MPa
Heat Deflection Temp.	105 - 175° C
Elongation Break	43%

Actual values may vary depending on build conditions.
Our technical team can advise.