

Image TBC

AME 8263



Vacuum Casting (VC)
Material Datasheet



UL94 SVA FAR 25 Compliant.

Measurement	Value
Shore Hardness	83D
Tensile Strength	68 MPa
Tensile Modulus	-
Flexural Strength	93 MPa
Flexural Modulus	2,200 MPa
Heat Deflection Temp.	80° C
Elongation Break	15%

Actual values may vary depending on build conditions.
Our technical team can advise.