

AME Clear



Liquid Crystal Display (LCD)
Material Datasheet



Produces translucent parts from a highly permeable resin.

Measurement	Value
Shore Hardness	78D
Tensile Strength	39 MPa
Tensile Modulus	1,702 MPa
Flexural Strength	53.5 MPa
Flexural Modulus	1,682 MPa
Heat Deflection Temp.	45.8° C
Elongation Break	7.8%

Actual values may vary depending on build conditions.
Our technical team can advise.