

AME PA 2210 FR



Selective Laser Sintering (SLS)
Material Datasheet



A high-performance, blue card certified SLS material with a halogen-free flame retardant.

Measurement	Value
Shore Hardness	75D
Tensile Strength	46 MPa
Tensile Modulus	2,500 MPa
Flexural Strength	65 MPa
Flexural Modulus	2,300 MPa
Heat Deflection Temp.	84° C
Elongation Break	4%

Actual values may vary depending on build conditions.
Our technical team can advise.