



REACTION INJECTION MOULDING (RIM) TECHNICAL PACK



MOMENTUM HOUSE
DINNINGTON, SHEFFIELD, S25 2RG

AME-3D.CO.UK
INFO@AME-3D.CO.UK | 01909 550 999



RIM CASTING



TECHNICAL SPECIFICATION

QUANTITY

Silicone Mould - Up to 50 | Hard Tooling - Up to 1000

Tolerances

0.3mm / 0.3% > 100mm

Wall Thickness

Min. 3mm

Letters & Logos

Min. 0.5mm

Gap between raised & recessed letters

Min. 0.5mm

Materials

AME 3829
AME 3838





MATERIAL	AME 3829	AME 3838
Description	A robust two-component polyurethane material that can be turned into bulk filler for the composite or construction industry at end of life.	Ideal for rapid prototyping and low volume production runs.
Available Colours	Black / Beige	Black
Rigid	x	x
High Temp.	x	x
Shore Hardness	82 - 86D	80 - 84D
Tensile Strength	43 - 47 MPa	35 - 40 MPa
Flexural Strength	63 - 67 MPa	53 - 58 MPa
Flexural Modulus	1,400 - 1,600 MPa	2,200 - 2,400 MPa
Heat Deflection Temp.	82 - 86° C	103 - 128° C
Elongation Break	5 - 7%	2.5 - 4%





AME 3829



Reaction Injection Moulding
(RIM)
Material Datasheet



Simulates thermoplastics like ABS and polypropylene.
Ideal for robust base units and under bonnet
components.

Measurement	Value
Shore Hardness	82 - 86D
Tensile Strength	43 - 47 MPa
Tensile Modulus	-
Flexural Strength	63 - 67 MPa
Flexural Modulus	1,400 - 1,600 MPa
Heat Deflection Temp.	82 - 86° C
Elongation Break	5 - 7%

Actual values may vary depending on build conditions. Our
technical team can advise.

Image TBC

AME 3838



Reaction Injection Moulding
(RIM)
Material Datasheet



Ideal for rapid prototyping and low volume production runs.

Measurement	Value
Shore Hardness	80 - 84D
Tensile Strength	35 - 40 MPa
Tensile Modulus	-
Flexural Strength	53 - 58 MPa
Flexural Modulus	2,200 - 2,400 MPa
Heat Deflection Temp.	103 - 128° C
Elongation Break	2.5 - 4%

Actual values may vary depending on build conditions. Our technical team can advise.