



AME Ultra RC70



A high-performance SLA resin that is strong & precise. Ideal for functional verifications or small batch terminal application scenarios.

Measurement	Value
Shore Hardness	85D
Tensile Strength	58 MPa
Tensile Modulus	1,950 MPa
Flexural Strength	72 MPa
Flexural Modulus	2,526 MPa
Heat Deflection Temp	59 - 70° C
Elongation Break	14%

Actual values may vary depending on build conditions. Our technical team can advise via info@ame-3d.co.uk.



SLA
Stereolithography
Material Datasheet

ame-3d.co.uk
Info@ame-3d.co.uk
01909 550 999



AME-3D
Realising in Three Dimensions