



Accura 25



A durable, polypropylene-like SLA material. Ideal for functional components including automotive styling parts.

Measurement	Value
Shore Hardness	80D
Tensile Strength	38 MPa
Tensile Modulus	1,590 - 1,660 MPa
Flexural Strength	55 - 58 MPa
Flexural Modulus	1,380 - 1,660 MPa
Heat Deflection Temp	51 - 63° C
Elongation Break	13 - 20%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.

