



Accura ClearVue



A transparent, polycarbonate-like material. It is well suited for automotive lenses, medical models, and visualisation models where transparency is key.

Measurement	Value
Shore Hardness	84D
Tensile Strength	41 - 46 MPa
Tensile Modulus	2,030 - 2,220 MPa
Flexural Strength	53 - 67 MPa
Flexural Modulus	1,560 - 2,040 MPa
Heat Deflection Temp	50 - 51° C
Elongation Break	4 - 7%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.

