



Somos® Waterclear Ultra



A SLA material with extraordinary optical clarity and high moisture resistance. It is well suited for automotive lenses, bottle and functional models.

Measurement	Value
Shore Hardness	87D
Tensile Strength	56 MPa
Tensile Modulus	2,880 MPa
Flexural Strength	84 MPa
Flexural Modulus	2,480 MPa
Heat Deflection Temp	43 - 47° C
Elongation Break	7.5%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.

