



AME Nylon PA 650



A versatile and highly robust material, which is chemical resistant and sustainable as 80% of post production powder is recyclable.

Measurement	Value
Shore Hardness	73D
Tensile Strength	48 MPa
Tensile Modulus	1,700 MPa
Flexural Strength	48 MPa
Flexural Modulus	1,500 MPa
Heat Deflection Temp	95 - 180° C
Elongation Break	24%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.



SLS
Selective Laser Sintering
Material Datasheet

ame-3d.co.uk
Info@ame-3d.co.uk
01909 550 999



AME-3D
Realising in Three Dimensions