



## Somos® EvoLVe 128



Stereolithography (SLA)  
Material Datasheet



A high-strength, ABS-like plastic. Ideal for low to medium part runs, large automotive rapid prototypes and medical devices.

Measurement	Value
Shore Hardness	82D
Tensile Strength	56.8 MPa
Tensile Modulus	2,964 MPa
Flexural Strength	74 MPa
Flexural Modulus	2,654 MPa
Heat Deflection Temp.	50 - 52° C
Elongation Break	11%

Actual values may vary depending on build conditions.  
Our technical team can advise.