



AME 8051



An ABS-type resin suitable for panels and enclosures. High temperature resistance with flexing properties.

Measurement	Value
Shore Hardness	77 - 84D
Tensile Strength	55.9 MPa
Tensile Modulus	2,150 MPa
Flexural Strength	85.9 MPa
Flexural Modulus	1,965 MPa
Heat Deflection Temp	92° C
Elongation Break	8%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.

