



AME PX234HT



A polyurethane resin that is suitable for prototypes & technical parts.

Measurement	Value
Shore Hardness	80D
Tensile Strength	61 MPa
Tensile Modulus	1,800 MPa
Flexural Strength	80 MPa
Flexural Modulus	1,850 MPa
Heat Deflection Temp	196° C
Elongation Break	13%

Actual values may vary depending on build conditions.
Our technical team can advise via info@ame-3d.co.uk.

