

WINDFORM XT



Selective Laser Sintering (SLS)
Material Datasheet



Excellent mechanical performances, including high stiffness matched to low density & remarkable lightness.

Measurement	Value
Shore Hardness	79D
Tensile Strength	83 - 84 MPa
Tensile Modulus	8928, 20 MPa
Flexural Strength	133, 00 MPa
Flexural Modulus	7338, 20 MPa
Heat Deflection Temp.	173, 40° C
Elongation Break	3, 80%

Actual values may vary depending on build conditions.
Our technical team can advise.